



Libra™ White RFU

RECOMMENDED PARAMETERS

Fabric Types



100% Polyester, Cotton and Poly/
Cotton blended fabrics

Mesh



Count: 80-225t/cm (31-88t/cm)
Tension: 18-35n/cm3

Squeegee



70 or 60-90-60
Profile: sharp, square
Stroke: x2 stroke, medium speed
Angle: 10-15%

Stencil



Standard Emulsion
Off Contact: 1/16" (2mm)
Emulsion Over Mesh: 40 micron

Flash & Cure



Flash: 300°F(149°C) for 4 seconds (on
preheated pallets)
Cure: 60 seconds at 270°F(132°C)

Pigment Loading



Not recommended

Libra™ Additives



Libra™ Catalyst: 3-5%
Libra™ Retardant: 0.5-3%

Storage



Store in sealed containers 12 months
from manufacture >40°F (5°C)
<77°F(25°C)

Clean Up



Standard plastisol cleaners

Health & Safety



Find SDS information here:
www.avient.com/resources/safety-data-sheets or contact your local CSR

Libra™ White RFU (LIB9062) is a medium viscosity extremely opaque white ink with a creamy texture, excellent printability and a matte effect for your silicone printing needs. The ink is designed to maximize opacity, bring excellent coverage and extreme stretchability while maintaining a super-soft flexible hand.

HIGHLIGHTS

- Matte finish
- Non-tacky hand
- Excellent coverage and opacity
- Super-soft hand feel
- Extreme stretchability
- Bright white

PRINTING TIPS

- Use 3-5 parts Libra™ Catalyst and 0.5-3 parts Libra™ Retardant to 100 parts Libra™ White RFU. Mix well and print. To prevent wastage only catalyze what is needed to print for 4 hours.
- Use 80-225t/cm (31-88t/cm) mesh screens for best performance.
- Print with 1/16" or 2mm off contact.
- Print two strokes to ensure the mesh is clear and you have a good ink deposit.
- Flash between prints.
- Clean the stencil area when stopped to prevent screen blockages.
- Prints should be cured at 270°F /132°C for 60 seconds. Check the cure temp at the ink surface.
- Test all prints for print durability before starting the production run.

COMPLIANCE

- Non-PVC, non-phthalate
- Visit www.avient.com/products/screen-printing-inks/zodiac-libra for more information

PRECAUTIONS

- The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications



AVIENT
SPECIALTY
INKS

V3.00 (Modified: 02/17/2021)