



12004PFXAB EPIC™ AMAZING BASE

WILFLEX™ Epic Amazing Base is a non-phthalate mixing base for manual and automatic screen printing on 100% cotton and cotton/poly blend substrates. Combining elements in design versatility and press performance, Amazing Base has been engineered to produce optimal color vibrancy and printability providing the versatility and performance you expect from a Wilflex Color System.

HIGHLIGHTS

- ✔ Clean, bright colors when mixed with Wilflex™ PCs or Equalizers
- ✔ Wet-on-wet printing at high production speeds with exceptional resistance to build-up
- ✔ Semi-opaque colors
- ✔ Satin finish
- ✔ Good color fastness to crocking test

PRINTING TIPS

- ✔ Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results
- ✔ When blended according to formulations, colors will be semi-opaque
- ✔ Exhibits good color reproduction on white garment and over a base plate. For some colors, base mixing systems are limited in color saturation and may require an increased ink deposit or formula adjustment to achieve accurate color
- ✔ Amazing Base is not a low-bleed ink; when printing on fabrics that are prone to bleed underbase with an approved WILFLEX low bleed white and/or blocker
- ✔ Exhibits good color retention in high-speed wet-on-wet production with exceptional resistance to build up
- ✔ Adjust flash cure temperature and dwell time so ink is just dry to touch. Depending on flash unit, a 2 - 3 second flash is adequate
- ✔ For cold-peel transfers, use a coated release paper or polyester film

COMPLIANCE

- ✔ Non-phthalate
- ✔ For individual compliance certifications and conformity statements, please visit: www.avient.com/wilflex-compliance

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications




AVIENT
SPECIALTY
INKS

V3.00 (Modified: 02/18/2021)

PRODUCT INFORMATION BULLETIN



RECOMMENDED PARAMETERS



Fabric Types

100% cotton, cotton/poly blends, some synthetics



Mesh

Count: 86-305 t/in (34-120 t/cm)
Tension: 25-35 n/cm²



Squeegee

60/90/60, 70/90/70, 60-90
Profile: Square, Sharp
Stroke: Medium flood, Medium-Fast stroke
Angle: 10-15%



Stencil

2 over 2
Off Contact: 1/16" (.2cm)
Emulsion Over Mesh: 15-20%



Flash & Cure

Flash: 220°F (105°C)
Cure: 300°F (149°C)



Pigment Loading



Wilflex™ Additives

Epic Viscosity Buster-1% max
Epic Finesse Base



Storage

65-90°F (18-32°C)
Avoid direct sunlight
Use within one year of receipt



Clean Up

Ink degradant or press wash



Health & Safety

Find SDS information here:
www.avient.com/resources/safety-data-sheets
or contact your local CSR

2021, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.