

PRODUCT INFORMATION BULLETIN

RECOMMENDED PARAMETERS

Fabric Types

100% polyester, polyester blends



Mesh

Count: 86-160 t/in (34-62 t/cm) Tension: 25-35 n/cm2



Squeegee

60/90/60, 60-70 Profile: Square, Sharp

Stroke: Hard flood, Medium stroke

Angle: 10-15%



Stencil

2 over 2 Off Contact: 1/16" (2mm) Emulsion Over Mesh: 15-20%



Flash & Cure

Flash: 220°F (105°C)

Cure: 320°F (160°C) Entire ink film



Pigment Loading



Wilflex™ Additives

Epic Viscosity Buster - 1% max



Storage

65-90°F (18-32°C) Avoid direct sunlight Use within one year of receipt



Clean Up

Ink degradant or press wash



Health & Safety

Find SDS information here: www.avient.com/resources/safety-data-sheets or contact your local CSR

16250PFXUBG EPIC™ ECHO UBG

Wilflex™ Epic Echo UBG is a non-phthalate ink designed to prevent dye migration when printed as an underbase on 100% polyester and poly blends. It provides the excellent bleed resistance along with good printability and coverage.

HIGHLIGHTS

Smooth surface with good hand, drape and W Works on a variety of fabrics fiber-matte down

Excellent bleed resistance

W Good printability

PRINTING TIPS

Stir inks before printing

W Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results

Print Echo UBG so that the flashed ink deposit fully covers the underlying fabric, avoid any fabric showing through the under base layer

Always overprint Echo UBG with a white and/or color systems for durability performance

Adjust flash cure temperature and dwell time so ink is just dry to touch. Depending on flash unit, a 2 - 3 second flash is adequate

COMPLIANCE

Non-phthalate

For individual compliance certifications and conformity statements, please visit: www.avient.com/wilflex-compliance

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications



AVIENT SPECIALTY

V3.00 (Modified: 02/18/2021)

2021, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the formation. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner