PRODUCT INFORMATION BULLETIN AVIENT SPECIALTY INKS 2582 INFINITE FX BRITTLE BASE **RECOMMENDED PARAMETERS** Avient[™] Specialty Inks INFINITE FX BRITTLE are specifically formulated inks that have the ability to easily fracture and crack when pressure is applied to the surface. Distorting the surface through **Fabric Types** bending or stretching causes the ink to crack and fracture. Brittle inks have a worn, tough finish that 100% cotton, cotton blends, some can resemble cracked paint or distressed appearance. synthetics **HIGHLIGHTS** Mesh > BRITTLE BASE | 2582 \$ Excellent adhesion to fabrics and wash BRITTLE WHITE | 11000 durability Count: 86-110 t/in (34-43 t/cm) Tension: 25-35 n/cm2 > Tough and hard wearing effect for a > Will not dry in the screen cracked paint or vintage look Squeegee > Tintable for infinite color combinations Durometer: 70/90/70, 70 Profile: Square, Sharp **PRINTING TIPS** Stroke: Hard flood, Slow stroke Angle: 10-15% \$ Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results. Recommended mesh counts can vary depending on particle size Stencil Print in last position or flash after each print if using multiple screens 2 over 2 Off Contact: 1/16" (.2cm) > Ink deposit is critical to achieve cracking results, use a print technique to assure a good ink Emulsion Over Mesh: 15-20% deposit and test for suitability Flash & Cure Print directly to fabric for best cracking results >> Flash: 220°F (105°C) Cure: 340-350°F (170-175°C) > Tintable with plastisol colorants. See Pigment Loading section for suggested starting tinting percentages \$ Cure between 340-350°F (170-175°C) and increase dwell time to assure cure and to achieve **Pigment Loading** desired cracking effect up to 5% Wilflex PC \$ After the print is cooled, "crack by hand" by stretching the printed area for a custom distressed up to 8% Wilflex EQ look up to 30% Wilflex RIO/MX up to 5% Rutland C3 Booster Additives 2910 VISCOSITY BUSTER - 1% max 2912 VISCOSITY BUSTER - 1% max Storage 65-90°F (18-32°C) COMPLIANCE Avoid direct sunlight Use within one year of receipt > Non-phthalate For individual compliance certifications and conformity statements, please visit \$ Clean Up www.avientspecialtyinks.com/services/compliance-support Dispose unused ink responsibly. Standard plastisol cleaners, press PRECAUTIONS wash, or ink degradant The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications **Health & Safety** Find SDS information here: AVIENT SPECIALTY www.avient.com/resources/safety-data-sheets V1.00 (Modified: 05/10/2021) or contact your local CSR INKS 2021, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of risk accuracy is the information and/or use or handling of any product. Avient makes no warranties or guarantees respecting suitability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information or products reflected by the ormation. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner