

AVIENT SPECIALTY INKS

PRODUCT INFORMATION BULLETIN



2584 INFINITE FX ROCK BASE

Avient™ Specialty Inks INFINITE FX ROCK BASE is specifically formulated for high density printing to create super hard textured effects such as solid rock, coarse rope, or fabric textured surfaces. Rock Base can be used alone or in combination with other Infinite FX bases to create various specialty effects.

HIGHLIGHTS

- ▶ Smooth or textured hard surface and excellent edge definition
- ▶ Excellent performance with providing structure and shape for HD prints
- ▶ Tintable for infinite color combinations
- ▶ Excellent adhesion to fabrics, stretch properties, and wash durability
- ▶ Use by itself or intermix with other Infinite FX Bases for unlimited design effects
- ▶ Suitable for high density or conventional flat screens

PRINTING TIPS

- ▶ Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results. Recommended mesh counts can vary depending on particle size
- ▶ For best HD results, use open mesh counts with 200 - 400 micron capillary film and print-flash-print. Use a heavy flood to fully fill the open areas of the stencil with ink then print with medium squeegee pressure
- ▶ Best when printed over a flash-dried underbase but suitable to be printed direct
- ▶ Adjust off-contact to imprint mesh patterns into Sculpture Base for textured feel and unique design effect
- ▶ Tintable with plastisol colorants. See Pigment Loading section for suggested starting tinting percentages

COMPLIANCE

- ▶ Non-phthalate
- ▶ For individual compliance certifications and conformity statements, please visit www.avientspecialtyinks.com/services/compliance-support

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications



AVIENT
SPECIALTY
INKS

V1.01 (Modified: 01/18/2022)

RECOMMENDED PARAMETERS



Fabric Types

100% cotton, cotton blends, some synthetics



Mesh

Count: 86-230 t/in (34-91 t/cm)
Tension: 25-35 n/cm²




Squeegee

Durometer: 70/90/70, 70
Profile: Square, Sharp
Stroke: Hard flood, Slow stroke
Angle: 10-15%



Stencil

2 over 2
Off Contact: 1/16" (.2cm)
Emulsion Over Mesh: 15-20% or 200-400 micron



Flash & Cure

Flash: 220°F (105°C)
Cure: 320°F (160°C)



Pigment Loading

up to 5% Wilflex PC
up to 8% Wilflex EQ or Rutland C3
up to 30% Wilflex RIO/MX or Rutland M3



Additives

2910 VISCOSITY BUSTER - 1% max
2912 VISCOSITY BUSTER - 1% max



Storage

65-90°F (18-32°C)
Avoid direct sunlight
Use within one year of receipt



Clean Up

Dispose unused ink responsibly.
Standard plastisol cleaners, press wash, or ink degradant



Health & Safety

Find SDS information here:
www.avient.com/resources/safety-data-sheets
or contact your local CSR

2021, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.