

Rutland™ LC9801 CHILL LC LOW BLEED WHITE



LC9801 Chill Low cure low bleed is a quick sheering ink for cotton/poly blends. This ink produces a low gloss to matte finish with a soft hand and excellent fiber mat-down. Chill LC LB exhibits a superior dye blocking on poly blends but prints brightly and smoothly on a wide range of fabrics. This low-puff dye blocking ink holds excellent detail and is capable of holding fine half tones.

Highlights

- Vibrant white with high opacity on dark fabrics
- Perfect for both vector and half tone prints
- Excellent for printing on manual and automatic presses
- This ink displays excellent elasticity, soft hand, and fabric drape
- Energy savings and cooler operating temperatures
- Shears down quickly to a very creamy smooth body retaining an even flood

Compliance

- Non-phthalate
- Internationally compliant
- Visit www.rutlandinc.com for more information











Precautions

- The information provided in this document is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications

Printing Tips

- Adjust flash cure temperature and dwell time so ink is just dry to touch. Avoid excessive flash temperatures to protect fabric and migration of dyes. Depending on flash unit, a 2 - 5 second flash is adequate.
- For best results, use a print-flash-print technique to ensure sufficient ink deposit on dark fabrics.
- Use 86–230t/in (34-90t/cm) mesh screens with high tension for best performance, ink release and opacity.
- Adjust your print parameters to allow this ink to clear fully on the second stroke using medium to low pressure for best dye blocking and opacity. As this ink shears down, less pressure will be required. Adjust accordingly.
- Curing is a time and temperature process. Using a lower temperature, at a lower belt speed will provide the best result without damaging the fabric.
- A behavior for high-opacity low cure inks is to "body-up" or gain viscosity when at rest. Be sure to "Pre-shear" or agitate this ink before use to achieve optimal flow before printing. Be careful to not use high-speed drills or similar equipment that will create friction-heat that can cause the ink to begin to cure. Store ink buckets up off of cold floors to reduce pre-shear time.
- Add up to 10% of LC0000 Chill Relax Extender to extend the LC colors and whites.

Recommended Parameters

 <p>Fabric Types Poly blends, 100% Polyester</p>	 <p>Flash & Cure Flash: 150° F (66° C) Cure: 270°-320° F (132° -160° C)</p>	 <p>Clean Up Non-phthalate press wash</p>
 <p>Mesh Count: 86- 230t/in (34 -90t/cm) Tension: 25-35n/cm²</p>	 <p>Pigment Loading N/A</p>	 <p>Health & Safety Find SDS information here: www.avient.com/resources/safety-data-sheets or contact your local CSR</p>
 <p>Squeegee Durometer: Medium: 60-70, 60/90/60 Profile: sharp, square Stroke: 2 stroke, medium speed Angle: 10°-15°</p>	 <p>Additives K2940 HUGGER CATALYST</p>	<p>2021, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.</p>
 <p>Stencil Standard Emulsion Off Contact: 1/16" (2mm) Emulsion Over Mesh: 15-20%</p>	 <p>Storage 65°-90°F (18°-32°C) Avoid direct sunlight. Use within one year of receipt. Keep container well sealed.</p>	



AVIENT
SPECIALTY
INKS

V1.00 (Modified: 18/03/2022)