

AVIENT SPECIALTY INKS

PRODUCT INFORMATION BULLETIN

2560 INFINITE FX NATURAL SUEDE BASE



Avient™ Specialty Inks NATURAL SUEDE BASE is specifically formulated to produce a soft, suede or velvet finish that is highly durable. Natural Suede can be combined with other Infinite FX bases to simulate leather or other textured surfaces.

RECOMMENDED PARAMETERS

HIGHLIGHTS

- Creates a printed graphic that feels like suede
- Use by itself or intermix with other Infinite FX Bases for unlimited design effects
- Tintable for infinite color combinations
- Suitable for high density or conventional flat screens
- Excellent adhesion to fabrics, stretch properties, and wash durability



Fabric Types

100% cotton, cotton blends, some synthetics



Mesh

Count: 86-230 t/in (34-91 t/cm)
Tension: 25-35 n/cm2



Squeegee

Durometer: 60/90/60, 60-70
Profile: Square, Sharp
Stroke: Hard flood, Medium stroke
Angle: 10-15%



Stencil

2 over 2
Off Contact: 1/16" (.2cm)
Emulsion Over Mesh: 15-20% or 200-400 micron



Flash & Cure

Flash: 220°F (105°C)
Cure: 320°F (160°C)



Pigment Loading

up to 10% Wilflex PC
up to 15% Wilflex EQ
up to 30% Wilflex MX/RIO
up to 30% Union RFU Colors
up to 15% Rutland C3 Boosters



Additives

N/A



Storage

65-90°F (18-32°C)
Avoid direct sunlight
Use within one year of receipt



Clean Up

Dispose unused ink responsibly. Standard plastisol cleaners, press wash, or ink degreasant



Health & Safety

Find SDS information here:
www.avient.com/resources/safety-data-sheets
or contact your local CSR

PRINTING TIPS

- Use consistent, high-tensioned screen mesh and sharp edged squeegees for best print results. Recommended mesh counts can vary depending on particle size
- For best HD results, use open mesh counts with 200 - 400 micron capillary film and print-flash-print. Use a heavy flood to fully fill the open areas of the stencil with ink then print with medium squeegee pressure
- Best results when printed directly onto fabric
- Tintable with plastisol colorants. See Pigment Loading section for suggested starting tinting percentages. Reduce the amount of white colorant in the formula as specialty base will lighten the color
- Adjusting cure temperature and dwell time will yield a variety of textured effects
- Cure between 340-350°F (170-175°C) and increase dwell time to assure cure and to achieve desired cracking effect
- After the print is cooled, "crack by hand" by stretching the printed area for a custom distressed look

COMPLIANCE

- Non-phthalate
- For individual compliance certifications and conformity statements, please visit www.avientspecialtyinks.com/services/compliance-support

PRECAUTIONS

The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications



AVIENT
SPECIALTY
INKS

V1.01 (Modified: 01/31/2023)

2022, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.