

WILFLEX™

Plastisol Screen Printing Ink





Choosing the best screen printing ink for substrate and brand performance can be overwhelming. Wilflex™ offers a broad portfolio of whites, standard colors, mixing systems, and specialty screen printing inks allowing screen printers to find the best inks for their most challenging projects. With an extensive range of inspired, cost-effective inks that meet the industry's strictest compliance standards, Wilflex makes it possible to excel in competitive marketplaces.

QUALITY AND CONSISTENCY

Wilflex™ products are produced to exacting standards and strict process procedures, ensuring quality and consistency of every batch.

Wilflex™ Epic™ inks are certified to **ZDHC Conformance Level 3** with **ECO PASSPORT by OEKO-TEX**. To learn more about compliance standards, please contact Avient Specialty Inks.*



PROFESSIONAL SUPPORT NETWORK

Knowledgeable and Highly Experienced Team

Our Avient Specialty Inks sales team has many years of experience in the screen printing industry to help you innovate and succeed, provide troubleshooting support, and solve technical problems you may encounter in your printing production environment. Our customer service team members are always ready to support ordering and fulfillment requests, ensuring a seamless customer experience.

Broad Distributor Network

Our extensive global network of distributors ensures Avient Specialty Inks products and services are available at your location and convenience.

Technical Expertise

We strive to help our customers stay ahead of marketplace trends and demands. Our qualified and experienced Avient Specialty Inks technical team is constantly looking at ways to improve our products' performance and to develop new technologies to meet emerging demands.

* Wilflex ECO PASSPORT certification numbers:
Wilflex 1.3 - 21.0.65055
Wilflex 2.10 - 21.0.70670

WHITE PLASTISOL INKS

Cotton Inks

- **Epic™ Echo Cotton White** is created with the large contract printer market in mind. It is characterized by its good fiber mat-down, brightness, matte appearance, and great value.
- **Epic™ Sprint White** is a premium ink that delivers superior printability and visual appearance. Epic Sprint White has an extremely fast flash time with minimal after-tack, excellent fiber mat-down, a smooth soft-hand, and bright finish.
- 💡 • **Epic™ Shock LC White** is a low cure premium ink that delivers superior printability with an ultra-soft, pliable, and bright finish. Epic Shock LC White has a fast flash and fast print strokes, making it ideal for high production print shops.

Nylon Inks

- 💡 • **Epic™ One-Step Nylon White** is created for printing on untreated nylon substances. Standard plastisol ink processes are recommended for this high opacity ink.

Polyester Inks

- **Epic™ Athletic Poly White** provides good resistance to dye migration and great coverage in polyester garments.
- 💡 • **Epic™ Rival Sport Victory White** is a high-performance, low bleed ink created for polyester sports apparel. Pair with the Rival Sport Victory Colors for printing polyester substrates that require low cure temperature.
- 💡 • **Epic™ PolyWhite LC Xtra** is a low cure ink with excellent bleed resistance and great coverage.
- 💡 • **Epic™ Performance LC White** combines best-in-class bleed resistance with ultra-stretch performance for a premium soft and pliable hand feel. It is created to print onto a variety of specialty fabrics, including compression wear, stretch garments containing spandex, lycra or elastane, polyester, blends, and triblend.

Poly-Cotton Blend Inks

- **Epic™ Echo LB White** is characterized by its opacity, good fiber mat-down, brightness, matte appearance, and great value. Epic Echo LB White is developed for applications on 100% cotton and poly-cotton blends where moderate bleed resistance is required.
- **Epic™ Quick White** delivers superior printability, premium aesthetics, an un-matched soft hand feel, and great fiber mat-down. It is characterized by an extremely fast flash time with minimal after-tack, fast print strokes, and easy mesh clearance for fast production environments.
- **Epic™ Amazing Bright Tiger White** is a low bleed white ink developed for applications where moderate bleed resistance is required. This white ink is press stable, giving printers flexibility to operate at a wide range of mesh counts, squeegee pressures, and pallet temperatures.
- 💡 • **Epic™ Bolt LC White** is a low cure white ink with great opacity. Pair with K2100 Epic Armor LC Gray as an underlay to obtain the best low-temperature dye migration resistance on all 100% polyester performance fabrics in the market today.
- 💡 • **Epic™ Single LC White** is a flexible cure, non-ghosting white ink for a variety of garment types. Single LC White is characterized by its excellent bleed resistance, stretch, and high opacity.



Flexible Cure Inks

- Inks and additives in Avient's Reduce portfolio reduce negative environmental impacts by using better, cleaner materials that consume fewer natural resources and generate less waste.
- 💡 • Avient Specialty Inks' reduced energy use portfolio is attributed with reducing energy consumption from typical alternatives, often resulting in decreased carbon emissions and lower energy costs. Achieve your sustainability goals with our flexible cure inks.

Avient offers a variety of low, or flexible, cure inks that can not only reduce energy consumption, but can also minimize dye migration and prevent shrinkage of heat-sensitive fabrics. These inks cure at temperatures as low as 270°F (132°C), as opposed to the standard 320°F (160°C) cure temperature of standard inks.

- **Epic Shock LC White, Epic Rival Sport Victory LC White, Epic PolyWhite LC Xtra, Epic Performance LC White, Epic Single LC White, Epic Shock LC White, Epic Nylon One-Step White, and Epic Bolt LC White** are classified as flexible cure white inks due to their reduced energy use capabilities.

PRINT GALLERY



Sustainability Spotlight



Reduced Energy Use

WHITE PLASTISOL INKS

CATEGORY	COTTON INKS			NYLON INKS	POLYESTER INKS				POLY-COTTON BLENDS				
Product Name	Epic Echo Cotton White	Epic Sprint White	 Epic Shock LC White	 Epic One-Step Nylon	Epic Athletic Poly White	 Epic Rival Sport Victory White	 Epic PolyWhite LC Xtra	 Epic Performance LC White	Epic Echo LB White	Epic Quick White	Epic Amazing Bright Tiger	 Epic Bolt LC White	 Epic Single LC White
Code	K2200	11335PFW	K2200	11000PFXOSN	K2200	K2200	K2200	K2200	K2200	11835PFW	K2200	K2200	K2200
Plastisol Type	Standard cure	Standard cure	Flexible cure	Flexible cure	Standard cure	Flexible cure	Flexible cure	Flexible cure	Standard cure	Standard cure	Standard cure	Flexible cure	Flexible cure
Colors	White	White	White	White	White	White	White	White	White	White	White	White	White
RECOMMENDED SUBSTRATES													
Cotton	Yes	Yes	Yes	No	No	No	No	Yes	Yes	Yes	No	No	Yes
Cotton/Polyeseter	No	No	No	No	Yes	Yes	Yes	Yes	Yes	Yes	Yes	Yes*	Yes
100% Polyester	No	No	No	No	Yes	Yes	Yes	Yes	No	No	No	Yes*	Yes
100% Untreated Nylon	No	No	No	Yes**	No	No	No	Yes	No	No	No	No	No
Nonwoven Polypropylene Bags	No	No	No	No	No	No	No	No	No	No	No	No	Yes
PROPERTIES & PERFORMANCE													
Opacity	Better	Better	Better	Better	Better	Best	Better	Best	Best	Better	Better	Best	Better
Bleed Resistance	N/A	N/A	N/A	N/A	Better	Best	Best	Best	Good	Better	Better	Best	Good
Hand	Better	Best	Better	Best	Good	Good	Good	Better	Good	Best	Better	Better	Good
Wet-on-Wet Capability	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended
APPLICATION													
Mesh	86–230 t/in (34–91 t/cm)	86–305 t/in (34–120 t/cm)	86–305 t/in (34–120 t/cm)	86–230 t/in (34–91 t/cm)	86–160 t/in (34–62 t/cm)	86–160 t/in (34–62 t/cm)	86–160 t/in (34–62 t/cm)	86–230 t/in (34–91 t/cm)	86–230 t/in (34–91 t/cm)	86–230 t/in (34–90t/cm)	86–280 t/in (34–110 t/cm)	86–305 t/in (34–120 t/cm)	86-230 t/in (34-90t/cm)
Flash	220°F (105°C)	220°F (105°C)	180°F (83°C)	180°F (83°C)	220°F (105°C)	180°F (83°C)	180°F (83°C)	180°F (80°C)	220°F (105°C)	220°F (105°C)	220°F (105°C)	180°F (83°C)	180°F (83°C)
Stencil	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct
Cure Temperature	320°F (160°C)	300°F (149°C)	270°F–320°F (132°C–160°C)	280°F (138°C)	320°F (160°C)	250°F–300°F (121°C–148°C)	250°F–300°F (121°C–148°C)	270°F (132°C)	320°F (160°C)	300°F (149°C)	300°F (149°C)	270°F–320°F (132°C–160°C)	260°F–280°F (127°C–138°C)
Wash	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant	Standard plastisol cleaners, press wash, or ink degredant
ADDITIVES													
Viscosity Reducer	ASI K2910 Viscosity Buster, 1–3% per weight	ASI K2910 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2910 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2910 Viscosity Buster, 1–3% per weight	ASI K2910 Viscosity Buster, 1–3% per weight	ASI K2910 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight
Bonding Agent	ASI K2940 hugger catalyst, 10% by weight	ASI K2940 hugger catalyst, 10% by weight	ASI K2940 hugger catalyst, 10% by weight	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	ASI K2940 hugger catalyst, 10% by weight
Extender	ASI K2920 FINESSE, 10% max by weight***	ASI K2920 FINESSE, 10% max by weight***	10340PFXFSB Epic Fashion Soft Base	Not recommended	ASI K2920 FINESSE, 10% max by weight***	10340PFXFSB Epic Fashion Soft Base	10340PFXFSB Epic Fashion Soft Base	10340PFXFSB Epic Fashion Soft Base	10340PFXFSB Epic Fashion Soft Base	ASI K2920 FINESSE, 10% max by weight***	ASI K2920 FINESSE, 10% max by weight***	ASI K2920 FINESSE, 10% max by weight***	10340PFXFSB Epic Fashion Soft Base

* When printing on 100% polyester, cure at 270°F (132°C) and pre-test for bleed resistance.

** Not suitable for all nylon substrates, pre-test prior to production.

*** Adding extender to any product will reduce opacity and performance.

COLOR SYSTEMS

Black Inks

- **Epic™ Matte Black** is a print black ink that produces a very low gloss surface appearance. Epic Matte Black offers exceptional print qualities for the manual and automatic printer due to its high-productivity, wet-on-wet printing capabilities.
- 💡 • **Epic™ Rival Sport Victory Black** delivers maximum coverage with the fewest strokes for color consistency when printing directly onto dark fabric or over an under base.
- 💡 • **Epic™ Rio RFU Black Diamond** is a flexible cure ink that offers superior opacity and wet-on-wet printing capabilities. Screen printers can achieve color quickly, even when using fine mesh screens.
- 💡 • **Epic™ One-Step Nylon Black** is created for printing on untreated nylon substances. Standard plastisol ink processes are recommended for this high opacity ink.

Standard Colors

- 💡 • **Epic™ Rio RFU Colors** offer a range of popular industry colors formulated to be vibrant, bold, and pure in color. Each color is optimized for unmatched quality and printability in a ready-for-use format. Rio RFU Colors are flexible cure and suitable for manual and automatic press.
- 💡 • **Epic™ Rival Sport Victory Colors** are low bleed and flexible cure colors that deliver maximum coverage when printing directly onto dark fabric or over an under base. With BSN Sports™ approved colors, Epic Rival Sport Victory offer superior on-press performance and exceptional print results.

Mixing Systems

- **Epic™ MX Color Mixing System** is an easy-to-mix color mixing with 17 translucent to semi-opaque intermixable colors. These Pantone®-simulated colors are developed for high production with a matte finish.
- 💡 • **Epic™ PC Express Color Mixing System** is an easy-to-use color mixing system with 15 intermixable pigment concentrates and a variety of mixing bases. Epic PC Express Color Mixing System enables printers to produce versatile Pantone® simulations for high production jobs.
- 💡 • **Epic™ Equalizer Color Mixing System** is an easy-printing color mixing system with 15 intermixable colorants and a base. The Epic Equalizer Color Mixing System allows printers to produce Pantone® simulations for high production projects.
- 💡 • **Epic™ Rio Mix** is a low cure finished ink mixing system formulated for an optimal balance of color accuracy and opacity. With 18 intermixable colors that enable printers to produce accurate Pantone® simulations, Epic Rio Mix is the most opaque color system in the line of Wilflex mixing color systems.



Flexible Cure Inks

- Epic Rio RFU Colors, Epic Rival Sport Victory Colors, Epic PC Express Color Mixing System, Epic Equalizer Color Mixing System, Epic Rio Mix, Epic Rival Sport Victory Black, Epic Rio RFU Black Diamond, and Epic One-Step Nylon Black are classified as flexible cure standard color inks due to their reduced energy use capabilities.




PRINT GALLERY

Wilflex mixing inks are available for use on IMS 3.0, a cloud-based solution for managing color and inventory in the textile screen-printing market. IMS manages daily maneuvers in a highly functional ink room by providing color management and communication agility, offering tools for color creation and standardizing.









Sustainability Spotlight



Reduced Energy Use



COLOR SYSTEMS

CATEGORY	BLACK INKS				STANDARD COLORS		MIXING SYSTEMS			
Product Name	Epic Matte Black	 Epic Rival Sport Victory Black	 Epic Rio RFU Black Diamond	 Epic One-Step Nylon	 Epic Rio RFU Colors	 Epic Rival Sport Victory Colors	Epic MX Mixing System	 Epic PC Express Color Mixing System	 Epic Equalizer Mixing System	 Epic Rio Mix
Code	19000PFX	19000	Epic Rio RFU	19000PFXOSN	Epic Rio RFU	Rival Sport Victory	Epic PF	Epic PC	Epic Equalizer	Epic Rio Mix
Plastisol Type	Standard cure	Flexible cure	Flexible cure	Flexible cure	Flexible cure	Flexible cure	Standard cure	Flexible cure	Flexible cure	Flexible cure
Colors	Black	Black	Black	Black	32 colors	22 colors	15 colors	15 colors	15 colors	18 colors

RECOMMENDED SUBSTRATES

Cotton	Yes	No	Yes	No	Yes	No	Yes	Yes	Yes	Yes
Cotton/Polyeseter	Yes	Yes	Yes	No	Yes	Yes	Yes	Yes	Yes	Yes
100% Polyester	Yes	Yes	Yes*	No	Yes*	Yes	No	Yes	Yes	Yes*
100% Untreated Nylon	No	Yes	No	Yes**	No	Yes	No	Yes	No	No
Nonwoven Polyproylene Bags	No	Yes	No	No	No	Yes	No	Yes	No	No

PROPERTIES & PERFORMANCE

Opacity	Good*	Good	Best	Better	Best	Better	Good	Better	Better	Best
Bleed Resistance	N/A	N/A	N/A	N/A	N/A	Best	N/A	Best	N/A	N/A
Hand	Better	Good	Best	Best	Best	Good	Best	Best	Better	Best
Wet-on-Wet Capability	Not recommended	Not recommended	Better	N/A	Better	Not recommended	Best	Best	Best	Better****

APPLICATION

Mesh	86–305 t/in (34–120 t/cm)	86–230 t/in (34–90t/cm)	110–305 t/in (43–120 t/cm)	86–230 t/in (34–91 t/cm)	110–305 t/in (43–120 t/cm)	86–230 t/in (34–90t/cm)	110–305 t/in (43–120 t/cm)	110–305 t/in (43–120 t/ cm)	110–305 t/in (43–120 t/cm)	110–305 t/in (43–120 t/cm)
Flash	160°F (70°C)	180°F (83°C)	180°F (83°C)	180°F (83°C)	180°F (83°C)	180°F (83°C)	220°F (105°C)	See base specifications	See base specifications	180°F (83°C)
Stencil	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct
Cure Temperature	320°F (160°C)	250°F–300°F (121°C–148°C)	266°F–320°F (130°C–160°C)	280°F (138°C)	266°F–320°F (130°C–160°C)	250°F–300°F (121°C–148°C)	320°F (160°C)	See base specifications	See base specifications	266°F–320°F (130°C–160°C)
Wash	Standard plastisol cleaners, press wash, or ink degraded	Standard plastisol cleaners, press wash, or ink degraded	Standard plastisol cleaners, press wash, or ink degraded	Standard plastisol cleaners, press wash, or ink degraded	Standard plastisol cleaners, press wash, or ink degraded	Standard plastisol cleaners, press wash, or ink degraded	Standard plastisol cleaners, press wash, or ink degraded	Standard plastisol cleaners, press wash, or ink degraded	Standard plastisol cleaners, press wash, or ink degraded	Standard plastisol cleaners, press wash, or ink degraded

ADDITIVES

Viscosity Reducer	ASI K2910 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2910 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight
Bonding Agent	ASI K2940 hugger catalyst, 10% by weight	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended	Not recommended
Extender	ASI K2920 FINESSE, 10% max by weight***	10340PFXFSB Epic Fashion Soft Base	10340PFXFSB Epic Fashion Soft Base	Not recommended	10340PFXFSB Epic Fashion Soft Base	10340PFXFSB Epic Fashion Soft Base	ASI K2920 FINESSE, 10% max by weight***	10340PFXFSB Epic Fashion Soft Base	10340PFXFSB Epic Fashion Soft Base	10340PFXFSB Epic Fashion Soft Base

* For one-hit opacity through coarse meshes, use a coating procedure that builds a thick, even stencil to ensure a good column height of ink.

** For bleed resistance, use an underbase white such as 11835PFW Epic Quick White, 11117PFW Epic Polywhite Xtra, LC Xtra, or K2200 Epic Athletic Poly White.

*** Refer to properties of selected base.

**** Use 230 mesh or higher for best wet-on-wet printing.

BASES AND OTHERS

Mixing Bases

- **Epic™ Mixing Base** is a high-productivity base for Epic PC and Epic Equalizer mixing systems. Epic Mixing Base offers exceptional print qualities for both manual and automatic prints.
- **Epic™ Amazing Base** is developed for manual and automatic screen printing with design versatility and press performance. Epic Amazing Base has been engineered to produce optimal color vibrancy and printability.
- **Epic™ Transflex Base** is used to create a soft-feel, hot-split transfer that gives the appearance of a direct print. Properly formulated colors will produce opaque prints on dark fabrics, without under-basing. Epic Transflex inks are created for fine line detail, solid spot color printing applications, and conventional cold-peel transfers.
- 💡 • **Epic™ LC Base** is created for manual and automatic screen printing with consistent color reproduction, excellent graphic durability, and efficient wet-on-wet application.
- 💡 • **Epic™ Rival Sport LC Base** is a low bleed, flexible cure mixing base for both manual and automatic printers. Combine a low bleed color system with the Rival Sport Victory White for additional bleed protection.
- 💡 • **Epic™ One-Step Nylon Base** is created for printing on untreated nylon substances. Standard plastisol ink processes are recommended for this high opacity ink.
- 💡 • **Epic™ Fashion Soft** is low cure, low viscosity plastisol base that simulates water-based ink printing and produces an ultra-soft hand feel. Fashion Soft can be mixed with colors or whites to soften the hand.

Bleed Blockers

- 💡 • **Epic™ Armor LC Gray** and **Epic™ Armor LC Black** are premium gray or black under base plastisol inks developed to fight even the toughest dye migration. Armor LC gives a smooth, creamy finish with great printability and easy mesh clearance.
- **Epic™ UBG** is bleed-resistant under base developed to prevent dye migration, while maintaining good printability and coverage.



Flexible Cure Inks

- **Epic LC Base, Epic Rival Sport LC Base, Epic Armor LC Gray, Epic Armor LC Black, Epic LC Base, Epic One-Step Nylon Base, and Epic Fashion Soft** are classified as flexible cure mixing bases and bleed blockers due to their reduced energy use capabilities.

PRINT GALLERY









Sustainability Spotlight



Reduced Energy Use

BASES AND OTHERS

CATEGORY								BLEED BLOCKERS		
Product Name	Epic Mixing Base	Epic Amazing Base	Epic Transflex Base	 Epic LC Base	 Epic Rival Sport LC Base	 Epic One-Step Nylon	 Epic Fashion Soft	 Epic Armor LC Gray	 Epic Armor LC Black	Epic UBG
Code	15000PFB	12004PFB	K2305	K2321	K2326	19930PFXOSN	10340PFXFSB	K2100	K2100	K2100
Plastisol Type	Standard cure	Standard cure	Standard cure	Flexible cure	Flexible cure	Flexible cure	Flexible cure	Flexible cure	Flexible cure	Standard cure
Colors	N/A	N/A	N/A	N/A	N/A	N/A	N/A	Gray	Black	Gray

RECOMMENDED SUBSTRATES										
Cotton	Yes	Yes	Yes	Yes	No	No	Yes	No	No	No
Cotton/Polyeseter	Yes	Yes	Yes	Yes	Yes	No	Yes	Yes	Yes	Yes
100% Polyester	No	No	No	No	Yes	No	No	Yes	Yes	Yes
100% Untreated Nylon	No	No	No	No	No	Yes**	No	No	No	No
Nonwoven Polypropylene Bags	No	No	No	No	No	No	No	No	No	No

PROPERTIES & PERFORMANCE										
Opacity	Better	Better	Good	Good	Better	Better	N/A	Best	Best	Better
Bleed Resistance	N/A	N/A	N/A	N/A	Better	N/A	N/A	Best	Best	Best
Hand	Better	Best	Best	Good	Good	Best	Best	Good	Good	Good
Wet-on-Wet Capability	Better	Best	Not recommended	Better	Not recommended	N/A	Better	Not recommended	Not recommended	Not recommended

APPLICATION										
Mesh	86–305 t/in (34–120 t/cm)	86–305 t/in	86–125 t/in (34–49 t/cm)	86–305 t/in (34–120 t/cm)	86–230 t/in (34–90 t/cm)	86–230 t/in (34–91 t/cm)	230–305 t/in (91–120 t/cm)	86–160 t/in (34–62 t/cm)	86–160 t/in (34–62 t/cm)	86–160 t/in (34–62 t/cm)
Flash	220°F (105°C)	220°F (105°C)	160°F (70°C)	180°F (83°C)	180°F (83°C)	180°F (83°C)	180°F (83°C)	180°F (83°C)	180°F (83°C)	180°F (83°C)
Stencil	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct	Direct
Cure Temperature	320°F (160°C)	300°F (149°C)	300°F (160°C)	270°F (132°C)	250°F–300°F (121°C–148°C)	280°F (138°C)	270°F–320°F (132°C–160°C)	270°F (132°C)	270°F (132°C)	320°F (160°C)
Wash	Standard plastisol cleaners, press wash, or ink degradant	Standard plastisol cleaners, press wash, or ink degradant	Standard plastisol cleaners, press wash, or ink degradant	Standard plastisol cleaners, press wash, or ink degradant	Standard plastisol cleaners, press wash, or ink degradant	Standard plastisol cleaners, press wash, or ink degradant	Standard plastisol cleaners, press wash, or ink degradant	Standard plastisol cleaners, press wash, or ink degradant	Standard plastisol cleaners, press wash, or ink degradant	Standard plastisol cleaners, press wash, or ink degradant

ADDITIVES										
Viscosity Reducer	ASI K2910 Viscosity Buster, 1–3% per weight	ASI K2910 Viscosity Buster, 1–3% per weight	Not recommended	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	Not recommended	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2912 Viscosity Buster, 1–3% per weight	ASI K2910 Viscosity Buster, 1–3% per weight
Bonding Agent	Not recommended	Not recommended	Not recommended	ASI K2940 hugger catalyst, 10% by weight	Not recommended	Not recommended	ASI K2940 hugger catalyst, 10% by weight	Not recommended	Not recommended	Not recommended
Extender	ASI K2920 FINESSE, 10% max by weight***	ASI K2920 FINESSE, 10% max by weight***	ASI K2920 FINESSE, 10% max by weight***	10340PFXFSB Epic Fashion Soft Base	10340PFXFSB Epic Fashion Soft Base	Not recommended	10340PFXFSB Epic Fashion Soft Base	10340PFXFSB Epic Fashion Soft Base	10340PFXFSB Epic Fashion Soft Base	ASI K2920 FINESSE, 10% max by weight***

* When printing on 100% polyester, cure at 270°F (132°C) and pre-test for bleed resistance.

** Not suitable for all nylon substrates, pre-test prior to production.

*** Adding extender to any product will reduce opacity and performance.

www.wilflex.com

Always test inks prior to production to ensure fitness for your particular application. Customer is responsible for proper application, suitability, and cure of all inks.

wilflex



1.844.4AVIENT
www.avient.com



Copyright © 2023, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.