




**WILFLEX™
WHITE SCREEN
PRINTING INK
PORTFOLIO**

Choosing the best white screen printing ink for substrate and brand performance requirements can be daunting. The Wilflex screen printing inks portfolio offers one of the broadest selections of white ink solutions for use on polyester, blends and 100% cotton to give printers access to an ink that will meet brand expectations. This guide outlines our complete offering of white ink, designed to print onto a variety of substrates, with a range of opacities, cure temperatures and application need.


COTTON

	Description	Opacity	Hand	Cure Temps	Bleed Resistance	Fiber Mat Down	Flash Time	Stretch
Echo Cotton White	<ul style="list-style-type: none"> Mainstream cotton white Maintains good opacity at high temperatures Suitable for long production runs 	Good	Best	320°F	Good	Best	Best	Better
Sprint White	<ul style="list-style-type: none"> Characterized by fast flash time Offers minimal after-tack and excellent mat-down 	Best	Best	300°F	Good	Best	Best	Best
Shock LC White 	<ul style="list-style-type: none"> Low curing properties Characterized by fast print strokes without compromising opacity 	Best	Good	270°F	Good	Good	Best	Better









DENOTES
PRODUCT
REDUCES
ENERGY USE




POLYESTER

	Description	Opacity	Hand	Cure Temps	Bleed Resistance	Fiber Mat Down	Flash Time	Stretch	Other Rec. Fabrics
Polywhite LC Xtra 	<ul style="list-style-type: none"> Wilflex best-in-class low bleed white ink Offers highest opacity rating in portfolio Printers can achieve full ink deposit 	Best	Good	250°F–300°F	Best	Best	Better	Good	100% polyester, triblends, polyester blends, cotton/poly blends
Rival Sport Victory LC White 	<ul style="list-style-type: none"> High performance low bleed ink Ideal for polyester sports apparel 	Better	Better	250°F–300°F	Best	Better	Best	Better	100% polyester, triblends, polyester blends, cotton/poly blends
Performance LC White 	<ul style="list-style-type: none"> Combines Wilflex best-in-class bleed resistance with ultra-stretch performance 	Best	Best	290°F	Best	Best	Better	Best	Compression wear, stretch garments containing spandex, lycra or elastane, polyester, blends and triblends
Single LC White 	<ul style="list-style-type: none"> Designed for universal low cure printing Developed to help printers simplify supply chain 	Best	Best	260°F–280°F	Better	Best	Best	Best	100% cotton, cotton blends, 100% polyester
Athletic Poly White	<ul style="list-style-type: none"> Mainstream white ink Offers bleed resistance, opacity and coverage 	Good	Good	320°F	N/A	Good	Better	Better	100% polyester, polyester blends



LOW BLEED

	Description	Opacity	Hand	Cure Temps	Bleed Resistance	Fiber Mat Down	Flash Time	Other Rec. Fabrics
Quick White	<ul style="list-style-type: none"> Premium white ink Characterized by fast flash time Ideal for fast production environments 	Best	Best	300°F	Best	Best	Best	100% cotton, cotton/poly blends
Amazing Bright Tiger White	<ul style="list-style-type: none"> Versatile white ink Commendable performance across a range of mesh screens Ideal for manual or automatic equipment 	Better	Better	300°F	Better	Best	Best	100% cotton, cotton/poly blends, triblends
Bolt LC White 	<ul style="list-style-type: none"> Low bleed and low cure ink Produces soft, subtle, bright and smooth finish 	Best	Best	270°F	Best	Best	Best	Polyblends, triblends, cotton/poly blends, 100% polyester, 100% cotton, non-woven polypropylene bags (NPB)
Echo LB White	<ul style="list-style-type: none"> Ideal for large contract printers Offers low bleed properties 	Better	Good	320°F	Good	Good	Good	Cotton/poly blends

For more information about Wilflex screen printing inks, please call **1.844.4AVIENT** or visit **www.wilflex.com**



www.avient.com

Copyright © 2023, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.