PRODUCT INFORMATION BULLETIN

Rutland[™] LC9802 CHILL LC COTTON WHITE



LC9802 Chill Cotton White is an optically brightened high opacity, high coverage, ink for 100% Cotton that is a great choice for vector and halftones. This ink offers excellent hand and fiber mat-down. Chill is fast flashing and holds fine detail while offering superior printability on both manual and automatic presses. Smooth printing and ultra soft, this white is excellent as a stand alone or top white.

Highlights		Printing Tip	S
Wide cure temperature range from 270°F/132°C to	o 320°F/160°C		printing for best flow.
Suitable as an under base or stand alone white		 Adjust flash cure terr 	nperature and dwell time so ink is just dry to touch but
Ideal for manual and automatic printing		tacky. Avoid excessive flash temperatures to protect fabric and migration of dyes.	
Excellent for both vector and half tone prints		• Use 86–230t/in (34-90t/cm) mesh screens with high tension for best performance, ink release and opacity.	
 Energy savings and cooler operating temperatures 		O Curing is a time and temperature process. Using a lower temperature, at a	
		lower belt speed will provide the best result without damaging the fabric. Lower cure does not mean you can increase belt speed. Ink still needs time to cure. 60 second dwell time/6-8 seconds at Cure temp.	
Superior drape and fiber mat-down and soft-hand.			n underbase flash white or as a hi-lite white.
Compliance	Sustainability	×	0000 Chill Relax Extender to extend the LC colors and
O Non-phthalate		whites.	
O Internationally compliant	Reduced Energy Use		
Visit https://www.avientspecialtyinks.com/ services/compliance-support	Ψ		
Precautions			
The information provided in this document is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate			
and application process to meet your customer sta	ndards and specifications		
Recommended Parameters			
Fabric Types	Flash & C	ure	Clean Up
O 100% Cotton	° F	(105°C) (132°C) Entire ink film	Non-phthalate press wash
			Health & Safety
Mesh Count: 86-305 t/in (34-120 t/cm)	Pigment I	Loading	Find SDS information here:
Tension: 25-35n/cm2			sheets or contact your local CSR
יווויר			2023, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for
Squeegee Durometer: Medium: 60-70, 70/90/70,	Additives	GER CATALYST	particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable
60/90/60 Profile: sharp, square Stroke: Hard flood, Fast stroke	K2912 VISCO	DSITY BUSTER LC	indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties;
Angle: 10°-15°	•		consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no
Stencil Storage			warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product
Off Contact: 1/16" (2mm) Emulsion Over Mesh: 15-20%		sunlight. ne year of receipt. ier well sealed.	performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES
♥			NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR
ÀVIENT AVIENT SPECIALTY INKS	V5.00 (Modified: 12/08/2023)		PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any
			patented invention without permission of the patent owner.