



W wilflex
SHOCK
LOW CURE WHITE COTTON



RIVAL
SPORT™



W wilflex
BOLT
LOW CURE WHITE LOW BLEED

➤ PRODUCT BULLETIN

Wilflex™ Low Cure White Inks

Wilflex™ low cure white inks are created to help screen printers reduce their energy use and increase productivity, while maintaining the opacity and brilliance needed for a high-quality white ink. These inks offer excellent printability and versatility, making them suitable for a wide range of fabric types and printing applications.

WILFLEX RIVAL SPORT LC WHITE

Fabric Type: Polyester

- **Low Cure Profile:** Cures at 250°F–300°F (121°C–148°C)
- **Athletic Printing Compatibility:** Ideal for polyester sports apparel and team sports numbers
- **Excellent Bleed Resistance:** Minimizes the risk of dye bleed at a wide temperature range

WILFLEX SHOCK LC WHITE

Fabric Type: 100% Cotton

- **Low Cure Profile:** Cures at 270°F–320°F (132°C–160°C)
- **Premium Soft Hand:** Provides a soft hand feel and excellent drape on 100% cotton garments
- **Fast Flash and Print Strokes:** Ideal for high-production print shops

WILFLEX BOLT LC WHITE

Fabric Type: Blends

- **Low Cure Profile:** Cures at 270°F–320°F (132°C–160°C)
- **High Opacity and Coverage:** Offers a brilliant white finish with superior coverage
- **Versatile Fabric Compatibility:** Performs well on poly-blends, triblends, cotton/poly blends, 100% polyester, and non-woven polypropylene bags

1.844.4AVIENT
www.avient.com



W wilflex™



AVIENT™

Copyright © 2025, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as “typical” or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient’s products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.