

## EH8099 MATTE BLACK



EH8099 MATTE BLACK is a press-ready black plastisol ink that does not "grey-out" with repeated washes. This ink has a contemporary matte finish that not only feels and looks more desirable, it will flash slightly faster than a glossy black ink.

## Highlights

- Easy to use, low pressure required.
- Terrific matte finish and excellent mat down.
- Remains black wash after wash when cured properly.

## Printing Tips

- Print on black garments for tone on tone images.
- EH8099 prints well through mesh ranges from 110-355 t/in (34-138 t/cm). Recommend 70-80 Durometer squeegee with sharp edge for maximum print definition.
- Printers should always test the ink on their fabric under their process conditions before printing production runs.
- In order to achieve maximum detail with black inks, consider splitting your black channel into 110-156 t/in mesh for vector areas and a second screen mesh of 305-355 t/in for halftones.












## Compliance

- Non-phthalate
- Internationally compliant
- Visit <https://www.avientspecialtyinks.com/services/compliance-support>

## Precautions

- The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications.

## Recommended Parameters

 <b>Fabric Types</b> Cotton	 <b>Flash &amp; Cure</b> Flash: 140-150°F on pre-heated pallets Cure: 320°F	 <b>Clean Up</b> Unused ink will need to be disposed of responsibly. Standard plastisol cleaners, press wash, or ink degradant
 <b>Mesh</b> Count: 110-355 t/in Tension: 18n-25n/cm3	 <b>Pigment Loading</b> N/A	 <b>Health &amp; Safety</b> Find SDS information here: <a href="http://www.avient.com/resources/safety-data-sheets">www.avient.com/resources/safety-data-sheets</a> or contact your local CSR
 <b>Squeegee</b> Durometer: 70,80 Profile: Square Stroke: 1+ Angle: 10-20%	 <b>Additives</b> K2940 HUGGER CATALYST	<p>2024, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.</p>
 <b>Stencil</b> Standard Emulsion Off Contact: 1/16" (2mm) or greater Emulsion Over Mesh: 15-20%	 <b>Storage</b> 65 -95° F (18 -35° C) Avoid direct sunlight. Use within one year of receipt. Keep container well sealed.	
	AVIENT SPECIALTY INKS	V5.10 (Modified: 05/07/2025)