

Wilflex™ Star™ Cotton White Great Value White Ink

Wilflex™ Star™ Cotton White provides excellent opacity, fiber mat down, and brightness to 100% cotton prints. This easy-to-print white ink stands out vividly on dark fabrics, giving your designs a clean and crisp look. It is excellent for vector and fine mesh halftone graphics.

HIGHLIGHTS

- High-performance cotton white at an affordable price
- User-friendly, tack-free formulation
- · Soft hand feel with great flexibility
- · Strong opacity
- · Excellent fiber mat down
- Manufactured in the UK

RECOMMENDED PARAMETERS

- Fabric type: 100% cotton
- Mesh Count: 34 to 61 t/cm (86 to 156 t/in)
- Flash: 120°C (248°F)
- Cure: 145°C (293°F)–160°C (320°F)



1.844.4AVIENT www.avient.com



Copyright © 2025, Avient Corporation. Avient makes no representations, guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application. You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES OR MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.