# **Rutland M3 Ink System**



M3 Ink Mixing System is an easy to use, highly accurate finished color matching ink mixing system. This system is much more forgiving than a PC based product as it does not require as accurate of measure or base and additives to complete a formula. Most formulas are combinations of M3 colors.

# **Highlights Printing Tips** M3 colors directly replace the M2 and EM ink mixing colors Printing on White Garments: Mix per formulation or by eye to achieve T brilliant colors on 100% cotton whites. M3 inks are opaque resulting in excellent coverage on dark garments For extremely soft-hand prints, mix finished color up to 1:1 with ES0250 Chino Base. The tack free formula allows printing through a range of mesh counts without the need for a viscosity modifier Printing on dark garments or over an underlay: When printing on dark 1 No build-up formulations ensure the highest print efficiencies without down garments, mix per formulation or custom blend to achieve brilliant colors over an underlay. time for wiping screens Mix thousands of finished ink colors by choosing Pantone colors from our IMS Use the Low Bleed White on poly/cotton blends and the ES0266 Barrier 3.0 Ink Mixing Software or by custom mixing your own colors Base when printing on 100% polyester. ES0266 Barrier Base available for printing on 100% polyester Puff designs: Mix up to 30% of K2470 NuPuff Base to any formulated color Compliance Non-phthalate Internationally compliant Visit https://www.avientspecialtyinks.com/ services/compliance-support **Precautions** The information above is given in good faith and does not release you from testing inks and fabrics to confirm suitability of substrate and application process to meet your customer standards and specifications. **Recommended Parameters**



# Fabric Types

Cotton



#### Flash & Cure

Flash: 140-150°F on pre-heated pallets

Cure: 320°F



#### Clean Up

Unused ink will need to be disposed of responsibly. Standard plastisol cleaners, press wash, or ink degradant



### Mesh

Count: 86-305 t/in Tension: 25n/cm3



### **Pigment Loading**

N/A



#### **Health & Safety**

Find SDS information here: www.avient.com/resources/safety-datasheets or contact your local CSR



#### Squeegee

Durometer: 70,80 Profile: Square Stroke: 1+ Angle: 15-20%



#### **Additives**

K2940 HUGGER CATALYST



# Stencil

Standard Emulsion Off Contact: 1/16" (2mm) or greater Emulsion Over Mesh: 15-20%



# Storage

65 -95° F (18 -35° C) Avoid direct sunlight. Use within one year of receipt. Keep container well sealed.



AVIENT SPECIALTY INKS

V5.10 (Modified: 06/11/2025)

2024. Avient Corporation, Avient makes no representations guarantees, or warranties of any kind with respect to the information contained in this document about its accuracy, suitability for particular applications, or the results obtained or obtainable using the information. Some of the information arises from laboratory work with small-scale equipment which may not provide a reliable indication of performance or properties obtained or obtainable on larger-scale equipment. Values reported as "typical" or stated without a range do not state minimum or maximum properties; consult your sales representative for property ranges and min/max specifications. Processing conditions can cause material properties to shift from the values stated in the information. Avient makes no warranties or guarantees respecting suitability of either Avient's products or the information for your process or end-use application You have the responsibility to conduct full-scale end-product performance testing to determine suitability in your application, and you assume all risk and liability arising from your use of the information and/or use or handling of any product. AVIENT MAKES NO WARRANTIES, EXPRESS OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE, either with respect to the information or products reflected by the information. This literature shall NOT operate as permission, recommendation, or inducement to practice any patented invention without permission of the patent owner.